

Elektrische Isolierstoffe Electrical insulating materials

Kennwerte Characteristic values

Typ Type	Glühdrahtentflammbarkeits- zahl (GWFI) Glow-wire flammability index (GWFI) DIN EN IEC 60695-2-12 (VDE 0471-2-12):2022-11; EN IEC 60695-2-12:2021	Glühdrahtentzündungs- temperatur (GWIT) Glow-wire ignition temperature (GWIT) DIN EN IEC 60695-2-13 (VDE 0471-2-13):2022-11; EN IEC 60695-2-13:2021	Vergleichszahl der Kriechwegbildung (CTI) Comparative tracking index (CTI) DIN EN IEC 60112 (VDE 0471-2-13):2022-11; EN IEC 60112:2020	Temperatur der Kugeldruckprüfung Temperature of the ball pressure test DIN EN 60695-10-2 (VDE 0303-11):2022-11; EN IEC 60695-10-2:2014	Farben Colours
LATAMID 6 H2PX-V2	825/0,75 825/1,5 825/3,0	775/0,75 775/1,5 775/3,0	---	---	Ungefärbt (reinweiß), weiss, schwarz uncoloured (white pure), white
LATAMID 6 H2PX-V2	775/0,75 775/1,5 775/3,0	775/0,75 775/1,5 775/3,0	---	---	schwarz black
LATAMID 6 H2PX-V2	850/0,75 850/1,5 850/3,0	775/0,75 775/1,5 775/3,0	---	---	rot red
LATAMID 6 H2PX-V2	---	---	325	180 °C	Alle Farben all colours